

Specification		Drury Lane		Super Drury Lane		Extra Super Drury Lane	
Construction		Tufted		Tufted		Tufted	
Pile yarn	BS4407	80% wool 20% nylon	(±3%)	80% wool 20% nylon	(±3%)	80% wool 20% nylon	(±3%)
Widths	BS3655	1m, 2m, 3m (cuts only) 4m, 5m (rolls and cuts)		1m, 2m, 3m (cuts only) 4m, 5m (rolls and cuts)		1m, 2m, 3m (cuts only) 4m, 5m (rolls and cuts)	
Pile density	BS4223	1492 tufts/100cm <sup>2</sup>	(±5%)	1571 tufts/100cm <sup>2</sup>	(±5%)	1858 tufts/100cm <sup>2</sup>	(±5%)
Rows	BS4223	379/m		399/m		472/m	
Machine gauge	BS4223	1/10		1/10		1/10	
Pile height above backing	BS4223	5.7 mm	(±0.5mm)	6 mm	(±0.5mm)	6.5 mm	(±0.5mm)
Finished Pile Weight	BS4223	1119 gms/m <sup>2</sup> 33 oz/yd <sup>2</sup>	(±5%)	1289 gms/m <sup>2</sup> 38 oz/yd <sup>2</sup>	(±5%)	1526 gms/m <sup>2</sup> 45 oz/yd <sup>2</sup>	(±5%)
Primary backing		Woven Polypropylene		Woven Polypropylene		Woven Polypropylene	
Backing material		Hessian		Hessian		Hessian	
Total carpet weight	BS4223	2122 gms/m <sup>2</sup>	(±10%)	2297 gms/m <sup>2</sup>	(±10%)	2529 gms/m <sup>2</sup>	(±10%)
Total carpet thickness	BS4223	9 mm	(±1mm)	9 mm	(±1mm)	9.5 mm	(±1mm)

## Performance

Wear classification	General Contract	Heavy Contract	Heavy Contract
---------------------	------------------	----------------	----------------

## Properties

Electrostatic		Low propensity to static down to 40% RH
Flame		If ignited from a single source such as a cigarette will self-extinguish
- Hot metal nut	BS4790/BS5287	Pass, low radius of ignition
- Methenamine pill	BS6307	Pass
Colour fastness		
- Light	BS1006	5
Biological attack		Mothproofed

## General Information

We reserve the right to change technical specifications without prior notice. Guaranteed colour match between all widths.

### Installation

To achieve maximum performance from this carpet, site conditions must comply with British Standards Specification BS5325. The carpet may be fitted in one of two ways:

- 1 For installations requiring more than one width or where subjected to castor chair, heavy or wheeled traffic the carpet must be fully adhered to the subfloor with or without the use of a special carpet underlay.
- 2 For smaller installations on underlay the use of a power stretcher is essential. Seams should be formed using hot melt or Silvaseam systems after pre-tensioning. On wooden cavity floors the use of paper lining laid beneath the underlay, along with skirting board sealer, is recommended to prevent dust penetration into the carpet.

### Maintenance

Vacuum for normal day to day cleaning. Spills and stains must be removed as part of a comprehensive maintenance plan including the use of dry or hot water extraction methods when required, depending upon local conditions.

Drury Lane products will provide maximum performance if installed and maintained in accordance with the recommendations set out in our installation and maintenance schedules, available on request.

### Special

Custom colours, carpet tiles or alternative backing options available - please refer to factory.

## Express samples

Additional samples are available for next day delivery upon request.



CONTRACT DIVISION

Unit 5, Wharfedale Business Park, Edward Street, Tong, Bradford BD4 9RT  
 Telephone: 01274 689114 Facsimile: 01274 689115  
 www.drurylanecarpets.co.uk E-mail: sales@drurylanecarpets.co.uk